



FLAG Cruising Extra Antifouling

PRODUCT DATA

Description:

Copper based antifouling free from booster biocides. This is a high performance (cruising grade) self eroding antifouling with proven performance within a wide variety of UK conditions including many European locations with medium fouling. Proven to create less 'build up' than many traditional antifouling. This product is self-priming when topping up existing (similar copper based) antifouling; otherwise FLAG Antifouling Primer is required. Suitable for general sailing and displacement craft up to around 8 knots.

Area of use:

Boat hulls

Substrates:

GRP, wood, steel and ferro cement. Not suitable for aluminum or galvanised surfaces.

Packing:

2.5 Litre

Physical Constants:

Colour: Black, Dark Blue, Light Blue, Red and Steel White

Finish: Matt

Volume solids: 68%

Theoretical spreading rate: 10 sq.metres per litre

Flash point: 42°C

Specific gravity: 1.65

Dry to touch: 2 hours

Over-coating time: 6 hours

**The theoretical spreading rate has been calculated for the stated volume solids and dry film thickness. A practical spreading rate will depend on the actual dry film thickness, the nature of the substrate, and the relevant consumption factor. The physical constants are subject to normal manufacturing tolerances.*

Application Details:

Application method: Brush Conventional spray Airless spray Roller

Thinner: FLAG Antifouling Thinners

Cleaning of tools: FLAG Antifouling Thinners

Surface condition: The surface should be stable, firm, dry and free of dust, sand, loose old paint, dirt, grease, oil and salt.

*Please refer to the Material Safety Data Sheet for further information.
For additional guidance please contact your local Technical Sales Representative.*

SAFETY: Handle with care. Before and during use, observe all safety labels on packaging and paint containers, consult Material Safety Data Sheets and follow all local or national safety regulations.